

Product Description

40% chopped glass fiber reinforced PPS, high flow, enhanced strength, excellent heat and chemical resistance

Material Properties

Properties	Test Method	Unit	chopped glass fiber reinforced	
			SG8L	SG8L-BK
Color	-	-	NA	Black
Density	ISO 1183	g/cm ³	1.66	1.66
Water Absorption	ISO 62	%	0.02	0.02
Mold Shrinkage Flow/Transverse	-	%	0.3/0.5	0.3/0.5
Tensile Strength	ISO 527	MPa	180	175
Elongation	ISO 527	%	1.5	1.5
Flexural Strength	ISO 178	MPa	250	240
Flexural Modulus	ISO 178	GPa	13.0	13.0
Notched Izod Impact	ISO 180	kJ/m ²	11.0	10.0
Heat Deflection Temperature 1.8 MPa	ISO 75	°C	260	260
Flammability Rating	UL-94	-	V0	V0

Notes for molding

Predry pellets at 120-140°C for 2-4 hours.

Temperature of mold at 130-150°C.

Optimum material temperature :290-320°C,Do not heat above 350°C.

Limit in-cylinder retention time: 300°C/60min. 320°C/30min.